


Solar Bronze 35 (Light)



Performance Data

Total Solar Energy Reduction	66%
Solar Energy Reflected	41%
Solar Energy Absorbed	39%
Solar Energy Transmittance	20%
Visible Light Transmittance	35%
Visible Light Reflected	29%
Ultra Violet Light Reflected	99%
Shading Coefficient	.39
Solar Heat Gain Coeff. (g Value)	.34
Emissivity	.68
Glare Reduction	61%



Performance Guide

Solar Heat Rejection	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
Glare Reduction	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
UV Reduction	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
Fade Reduction	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
Safety & Security	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
One-Way Privacy	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
Two-Way Privacy	☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
Scratch Resistance Coating	Yes
Warranty Period	10 Years

Key:

Excellent ☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️ Some Benefit ☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️
N/A ☀️☀️☀️☀️☀️☀️☀️☀️☀️☀️

Window Film Notes

An very good solar reflective sputtered film with a warm copper appearance .



T: 01428 751004
E: sales@solarcontrol.co.uk
W: www.solarcontrol.co.uk